

The LAWRENCE-McFADDEN CO.



Established 1875 - Incorporated 1899
INDUSTRIAL FINISHING PRODUCTS

7430 STATE ROAD
Philadelphia, Pennsylvania 19136

R-1724 **LOW HAPS BUTYRATE SEALER**

R-1724 is a catalyzed sealer which offers improved adhesion and moisture resistance over conventional non-catalyzed sealer, and is recommended for use under conversion varnish.

Physical Properties

| | |
|-------------------|---|
| Viscosity | 20" #2 Zahn Cup @ 77 degree F |
| Solids Content | 30% by weight |
| Weight per Gallon | 7.5 lbs. per gallon |
| Catalyst | 2 ounces per gallon CV-2526 or 4 ounces per gallon CV-1152 or 2 ounces CV-1152 + 1 ounce CV-2526/gallon |
| Pot Life | 14 days, depending on ambient temperature and catalyst used. |
| HAPS | 0.5 lbs. HAPS/lb of solids |
| VOC | 5.11 lb/gallon minus exempts |

Film Properties

| | |
|--------------|--|
| Cold Check | Depends on what topcoat is used. Normally, 20 cycles with a quality topcoat |
| Adhesion | Depends on stain and topcoat. Usually 8/10 kg passed on balance beam adhesion test. |
| UV Stability | Excellent Non-Yellowing |

Drying Time

| | |
|-------------|------------|
| Tack Free | 10 minutes |
| Dry to Sand | 45 minutes |

The LAWRENCE-McFADDEN CO.



Established 1875 - Incorporated 1899

INDUSTRIAL FINISHING PRODUCTS

7430 STATE ROAD

Philadelphia, Pennsylvania 19136